

Hot Stamp

SUPPLY COMPANY

TECHNICAL DATA SHEET

Series: BW88

Substrate		Die Temperature Range
ABS	Paper	220-275° F Metal
Acetate	Parchment	105-135° C Metal
Acrylic	Polyester	
Aqueous Coated Stocks	Polyurethane	
Cloth	Pyroxylin	Carrier
Lacquered Wood	Rigid PVC	12 Micron (48ga.)
Leather	Stain Ribbon	Polyester Film

Series: YED

Substrate		Die Temperature Range
Acetate	Polystyrene	220-300° F Metal
Acrylic	Propinate	104-149° C Metal
Cellophane (Seran Ctd)	Polyester	250-425° F Silicone
Lacquered Wood	Polyurethane	121-218° C Silicone
Leather (Coated)	Pyroxylin	Carrier
Paper (Ctd and Unctd)	Rigid PVC	12 Micron (48ga.)
Polycarbonate	Stain Ribbon	Polyester Film

Series: LFQ

Substrate		Die Temperature Range
Acetate Laminated Stock	Leather (Coated)	250-350° F Metal
Book Stock	Leather (Uncoated)	120-180° C Metal
Kromekote	Pyroxlin	
Dry Paper Stock	Satin Ribbon	
Inked/Lacquered Stock	Velour Ppr Stock	Carrier
Lacquered Wood	UV Coated	16 Micron (60ga.)
Labeled Stock (Self-Adh)		Polyester Film