

# GED HIGH GLOSS PIGMENT

## SUBSTRATES

Polystyrene, ABS, SAN  
Acrylic, Butyrate, Rigid Vinyl  
Acetate, Delrin, Nylon, Noryl  
Coated Wood, Polycarbonate

## RECOMMENDED STAMPING CONDITIONS

Temperature                      400 F – 450 F    Silicone  
   260 F – 350 F    Metal

## PHYSICAL PROPERTIES

Carrier:                              Polyester  
Application Area:                Fine to Broad

## SPECIAL FEATURES

This series is a high gloss finished foil formulated to hot stamp a wide variety of substrates. This series offers sharp, clean imprints, excellent scratch and mar resistance. No top rub or bleeding.

## COMMON APPLICATIONS

Appliances, cosmetic containers, or any application where durability is a factor.

